

TECHNICAL DATA SHEET



ULTRA LIGHT FILLER

A non shrinking, non slumping ready to use ultra light filling paste. After curing this product is sandable and paintable with most paints.

USES: For filling large and small holes and gaps in static joints in one application. Horizontal and vertical applications will not slump, making it particularly good for filling holes in ceilings. Can be used on concrete, brickwork, plasterboard and wood.

COLOUR: White

PACKAGING: 500ml packed 1 x 12
1 Litre packed 1 x 6
4 Litre packed 1 x 2

PREPARATION

Surfaces must be clean, dry and free of dust.

APPLICATION

Apply with a putty knife making sure the hole is completely filled and that the surface is smoothed off.

FINISHING

Sureseal Ultra Light Weight Filler can normally be painted over within 15 minutes of application, or when touch dry with alkyd and water based paints. When painting over with oil based paints, allow the filler to dry for 12 hours before painting. After use clean the knife with water. Ensure the packaging is closed tight.

SURESEAL ULTRA LIGHT FILLER TECHNICAL DATA SHEET CONTINUED

HEALTH & SAFETY

Keep out of reach of children. Wear suitable protective clothing, gloves and eye/ face protection. Dispose of empty packaging correctly.

LIMITATIONS

Among others not suitable for use on bituminous or substrates that extrude oil, plasticizers or solvents. Not suitable for submerged joints or areas exposed to high abrasion. Painting over with highly filled emulsion paints can cause cracks in the paint. Adhesion and paint tests prior to application are recommended. It is the users responsibility to determine suitability.

LIABILITY

The information given is the result of our tests and experience and is believed to be accurate and reliable. However as Siroflex Limited cannot know all the uses its products may be put to, and as application methods are out of our control it is the users responsibility to determine suitability of use.

TECHNICAL DATA	SURESEAL ULTRA LIGHT FILLER
Form	Ready to use thixotropic pasta
Cure System	Water based
Colour	White
Specific gravity	0.30 – 0.35
pH	7.5 to 9.0
SAG	none
Open time	15 minutes
Solids	>60%
Application temperature	+4°C to + 30°C
Service temperature	-15°C to +75°C
Durability	15 years
Shelf Life	Up to 15 months when stored unopened in cool dry conditions. Avoid extremes of temperature.

Full health and safety data information can be downloaded from www.siroflex.co.uk.

Issue1/0251.0.P/ 04.11.10/DR